

Description

Waterborne sealer for end grains.

General Notes

Main characteristics:

- Waterborne.
- Quick drying.
- Good adhesion to wood and primers.
- Translucent.
- Great ease of application.

Use:

In joinery industries as a sealer for end grains to be finished with opaque/translucent waterborne and oil alkyd joinery products.

Application Data

Conditions of application:

Application temperature: 10-30°C.
Relative humidity: maximum 85%.

Method:

Gap gun, putty knife.

Thinning:

Water if necessary.

Cleaning of equipment:

Clean in water promptly after use. Add detergent if required.

Recommended film thickness:

Not applicable.

Coverage rate:

Not applicable.

Drying times at 20°C/
65% relative humidity:

Dust dry: after approximately 1 hour.
Recoatable: after approximately 3 hours.

**All coatings must be thoroughly dry before applying a further coat.
Low temperatures and/or high humidity can delay drying times.**

Practical Application Data

See application information by specific area. Refer to Index.

Properties

Viscosity:

Thixotropic paste.

Density:

Approximately 1.03kg/dm³.

Solids content:

Approximately 32% by weight = approximately 29% by volume.

Gloss level:

Not applicable.

Flow:

Not applicable.

Adhesion:

Excellent.

Weather resistance:

Applications of Kodrin WV456 should be finished before being exposed outside.

Further Information

Container sizes:	310ml tube (6 x 310ml), 750ml Tub (6 x 750ml).
Minimum shelf life:	12 months if stored in unopened packing.
Storage:	Store in a cool and frost free place.
Colour range:	Colourless.

Health and Safety Aspects

Flash point (DIN 53213):	> 100°C.
HAZECHEM:	Not applicable.
Transport Code:	Not applicable.
Labelling:	Health and safety information according to EEC directive: S02: Keep out of reach of children. S51: Use only in well ventilated areas. S46: If swallowed, seek medical advice immediately and show the container label or this sheet.
Government regulations:	The user of this product is required to comply with the national statutory regulations for health and safety at work and waste disposal.
Ventilation requirements:	MVR: 50 10%LEL: 5 Minimum Ventilation Requirement in m ³ air/litre paint to keep below Occupational Exposure Limits of the product. 10%LEL = Amount in m ³ air/litre paint to keep below 10% of the Lower Explosion Limit.

Please Note

- Every care is taken to ensure that the information provided in this data sheet is accurate. Jac Jay Limited is unable to guarantee results as it has no control over the conditions under which products are applied, the substrate or the application. The customer has to determine the suitability of the delivered products or information for its intended purpose.